

EpoxAcast® 670 HT

High Temp Castable Epoxy



www.smooth-on.com

PRODUCT OVERVIEW

EpoxAcast® 670 HT (formerly 20-136) is an epoxy casting compound which offers high heat resistance up to 350° F/177° C if post cure schedule is used. **EpoxAcast® 670 HT** features a relatively low viscosity that ensures minimal bubble entrapment. **EpoxAcast® 670 HT** also offers an extra long working time of 3 hours. Castings cure with negligible shrinkage and are very hard, very strong and heat resistant. **EpoxAcast® 670 HT** is ideal for making vacuum form molds, foundry patterns, forming dies & fixtures, hard rollers, industrial parts and high impact tools. **EpoxAcast® 670 HT** is also suitable for encapsulation applications or for use as a high temperature epoxy for bonding a variety of surfaces.

PRODUCT SPECIFICATIONS

EpoxAcast® 670 HT High Temp Castable Epoxy	
Handling Properties	
Mix Ratio By Weight	100 A : 16 B
Mixed Viscosity - cps. (ASTM D2393)	6,000
Specific Gravity - Mixed; g./c.c. (ASTM D1475)	1.15
Spec. Volume - Mixed; cu. in./lb. (ASTM D792)	20.51
Pot Life* (ASTM D2471)	3 Hours
Cure Time*	24 Hours followed by: Heat cure for 2 hrs at 175°F/80°C followed by 3 hrs at 300°F/150°C
Color - Mixed	Beige
Physical Properties	
Shore D Hardness (ASTM D2240)	90
Ultimate Tensile - psi (ASTM D638)	4,500
Tensile Modulus - psi (ASTM D638)	332,000
Tensile Elongation (ASTM D638)	0.65%
Flexural Strength - psi (ASTM D790)	11,000
Flexural Modulus - psi (ASTM D790)	254,000
Compressive Strength - psi (ASTM D695)	13,000
Compressive Modulus - psi (ASTM D695)	101,400
Heat Deflection Temp. (ASTM D648)	
If cured at room temperature	252° F / 122° C
if post cured according to heat curing schedule	350° F / 177° C

Volume Resistance (ohm) (ASTM D257-99): >5.42E+11
Volume Resistivity (ohm cm) (ASTM D257-99): >3.59E+15
Dielectric Constant k' @ 60 Hz (ASTM D150-98): 5.3
Dielectric Constant k' @ 1 kHz (ASTM D150-98): 5.08
Dielectric Strength (V/mil) (ASTM D-147-97a): 404

All values measured after 7 days at 73°F / 23°C
 *Pot Life and Cure Time values are dependent on mass and mold configuration, as epoxies are mass-sensitive.

PROCESSING RECOMMENDATIONS

Preparation – Avoid breathing fumes - use in a well ventilated area at minimum. NIOSH approved respirator is recommended. Wear safety glasses, long sleeves and rubber gloves to minimize skin contact.

Materials should be stored and used in a room temperature environment (73°F/23°C). Elevated temperatures will reduce pot life. EpoxAcast® 670 HT Resin and Hardener must be properly measured and thoroughly mixed to achieve full, high-strength, solid-cure properties. ***Because no two applications are quite the same, a small test application to determine suitability for your project is recommended if performance of this material is in question.***

Applying A Release Agent – This product is adhesive and will bond to many surfaces. For epoxy to epoxy applications where adhesion is not desired, an application of paste wax followed by Ease Release® 2125 PVA available from Smooth-On may be used. For other surfaces such as metal or plastic, a silicone based spray release such as Universal® Mold Release also available from Smooth-On may be used to prevent adhesion.

Pre-mix Part A Thoroughly - Separation may have occurred in transit or storage. Pre-mix for 2 minutes prior to dispensing to a uniform consistency using a straight edge paddle (paint stirrer) or turbo mixer (drill attachment).

Measuring / Dispensing – Accurate measurement by weight is required for the material to cure properly and develop full physical properties. Dispense Parts A and B in proper proportions into clean plastic, metal or wax-free paper containers. **You must use an accurate scale (gram scale or triple beam balance scale) to weigh these components properly. Do not attempt to measure components by volume.**

Safety First!

The material safety data sheet (MSDS) for this or any Smooth-On product should be read before using and is available on request. All Smooth-On products are safe to use if directions are read and followed carefully.

EpoxAcast® 670 HT Resin PART A:

WARNING: IRRITANT TO EYES, SKIN & MUCOUS MEMBRANES.

EpoxAcast® 670 HT Resin is irritating to the eyes and skin. Avoid prolonged or repeated skin contact to prevent possible sensitization. Avoid breathing vapors and use only with adequate ventilation. Wear personal protective equipment.

First Aid: In case of eye contact, flush thoroughly with water for 15 minutes and get immediate medical attention. In case of skin contact, wipe clean with white vinegar and wash thoroughly with soap and water. If irritation persists, get medical attention. If swallowed, do not induce vomiting. Drink 1 - 2 glasses of water and get immediate medical attention. If vapors are inhaled or if breathing becomes difficult, remove person to fresh air. If symptoms persist, get medical attention.

Keep Out Of Reach Of Children.

EpoxAcast® 670 HT Hardener PART B:

WARNING: IRRITANT TO EYES, SKIN & MUCOUS MEMBRANES.

EpoxAcast® 670 HT Hardener is corrosive, causing severe skin and eye burns. Avoid prolonged or repeated skin contact to prevent possible sensitization. Use only with adequate ventilation. If contaminated flush eyes with water for 15 minutes and seek medical attention. Remove from skin with waterless hand cleaner then soap and water. Refer to MSDS. **First Aid:** In case of eye contact, flush thoroughly with water for 15 minutes and get immediate medical attention.

Keep Out Of Reach Of Children.

IMPORTANT: The information contained in this bulletin is considered accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results to be obtained from the use thereof, or that any such use will not infringe upon a patent. User shall determine the suitability of the product for the intended application and assume all risk and liability whatsoever in connection therewith.

Adding Color & Fillers - EpoxAcast® 670 HT can be colored with SO-Strong® color tints (from Smooth-On). Pre-mix tint with Part A thoroughly and then add Part B. A variety of dry fillers can also be added. Pre-mix dry filler with Part A before adding Part B.

Mixing - Be sure mixing utensils are clean and free of any potential contaminants such as dirt, dust or grease. Mix Parts A and B thoroughly for at least 3 minutes with a square edged mixing stick. Be aggressive and scrape sides and bottom of mixing container several times. Use the square edge of mixing stick to bring material off of the sides of container and blend. **If using a drill mixer**, follow with hand mixing as directed above to ensure thorough mixing.

Vacuuming - EpoxAcast® 670 HT is low in viscosity compared to other epoxy coating systems and does not require vacuum degassing. If you choose to vacuum the material, subject mixture to 29 h.i.g. mercury in a vacuum chamber until mixture rises, breaks and falls. Allow for 5 times volume expansion in mixing container.

Pouring - If casting EpoxAcast® 670 HT into a rubber mold, pour mixture in a single spot at the lowest point of the mold. Let the mixture seek its own level. A uniform flow will help minimize entrapped air.

If making vacuum forming molds, it is best to use piano wire (15/1000 inch gauge) to make vacuum holes.

Cure Time: Refer to specified **Cure Times** in **Handling Properties** section. Cured material will be hard and unable to penetrate with a finger nail. Cured epoxy can now be dry sanded. **If machining or sanding, wear NIOSH approved mask to prevent inhalation of particles. Pot life and cure time values are dependent on mass and mold configuration, as epoxies are mass-sensitive.**

Heat Curing - For best results, EpoxAcast® 670 HT should be heat cured in a dedicated industrial oven. Cure at 175° F / 80° C for two hours, followed by three hours at 300° F / 150° C. Allow material to cool to room temperature before use.

Painting - Cured EpoxAcast® 670 HT can be painted or primed and then painted with acrylic enamel paints. Let paint fully dry before putting part into service.

Removing Epoxy - Uncured / Non-curing epoxy: Scrape as much material as possible from the surface using a scraper. Clean the residue with E-POX-EE KLEENER® available from Smooth-On, lacquer thinner, acetone or alcohol. Follow safety warnings pertaining to solvents and provide adequate ventilation.



Call Us Anytime With Questions About Your Application

Toll-free: (800) 762-0744 Fax: (610) 252-6200

The new www.smooth-on.com is loaded with information about mold making, casting and more.